

## CHP 170 Cut Test

A cut test was executed on 3 cutting points on the blade area of the CHP-170 cutter using 16 awg copper wire. The hand tool executed with no breaking or trauma after 1,000,000 cuts. The average cutting force needed 4.9 kg. Please see attached document for further information.

HakkoUSA Knowledge Base

<https://kb.hakkousa.com/Knowledgebase/11684/CHP-170-Cut-Test>